

GREASE COMPATIBILITY CHARTS

General Grease Compatibility Chart

	Aluminum Complex	Barium	Calcium	Calcium 12-Hydroxy	Calcium Complex	Calcium Sulfate	Clay	Lithium	Lithium 12-Hydroxy	Lithium Complex	Polyurea	Silicone
Aluminum Complex	X	I	I	C	I	I	I	I	I	C	I	I
Barium	I	X	I	C	I	B	I	I	I	I	I	I
Calcium	I	I	X	C	I	-	I	I	I	C	I	I
Calcium 12-Hydroxy	C	C	C	X	B	-	C	C	C	C	I	I
Calcium Complex	I	I	I	B	X	C	I	I	I	C	C	I
Calcium Sulfate	I	B	-	-	C	X	I	C	C	C	I	I
Clay	I	I	C	C	I	I	X	I	I	I	I	I
Lithium	I	I	C	C	I	C	I	X	C	C	I	I
Lithium 12-Hydroxy	I	I	B	C	I	C	I	C	X	C	I	I
Lithium Complex	C	I	C	C	C	C	I	C	C	X	I	I
Polyurea	I	I	I	I	C	I	I	I	I	I	X	I
Silicone	I	I	I	I	I	I	I	I	I	I	I	X

Source: E.H. Meyers' paper entitled "Incompatibility of Greases" 49th Annual NLGI Meeting

C = Compatible

B = Borderline Compatible

Typically results in a light softening or hardening of the NLGI Grade and a lowering of the dropping point of the mixture of grease.

I = Incompatible

Typically results in a softening or hardening of greater than 1 1/2 the NLGI grade, a shift in the dropping point, and a possible reaction of additives or base oils.

Royal Purple Ultra-Performance® Grease Compatibility Chart

	Aluminum Complex	Barium	Calcium	Calcium 12-Hydroxy	Calcium Complex	Clay	Lithium	Lithium 12-Hydroxy	Lithium Complex	Polyurea	Silicone
Operating Temps. <225°F	C	C	C	C	C	I	C	C	C	C	I
Operating Temps. 225-350°F	C	B	B	C	B	I	B	B	C	B	I
Operating Temps. >350°F	C	I	I	C	I	I	I	I	C	I	I

Note: Ultra-Performance® greases are more stable. This chart is generated from independent lab testing and field experience. Actual compatibility results may vary. It is recommended that bearings be purged of old grease per OEM instructions to ensure proper lubrication and performance.

Industrial Sealing & Lubrication, Inc.
15430 S. Keeler St. Olathe, KS 66062

Local: 913-334-5823 Toll Free: 1-800-431-5823 Fax: 1-866-244-8684 Email: info@indsealing.com